

X 25 Year System Warranty

X Internal External Grade

X Sequentially Metre Marked


X Bend insensitive fibre core

### Features

- 25 Year System Warranty
- Sequentially Metre Marked
- LSOH Black Sheath
- Bend insensitive fibre core
- Internal External Grade
- 50/125 Multimode Fibre
- 500 MHz.km Bandwidth
- Cut to length service

### Product Overview

Excel tight buffered optical fibre cables have been designed specifically for internal and external applications. With the new bend insensitive core construction these compact, lightweight cables are extremely flexible and quick and easy to install. The cables are constructed around swellable reinforced yarns as common strength containing up to 24 colour coded 900µm tight buffered 50/125µm fibres, covered with a flame retardant, low smoke zero halogen, outer sheath.



### Performance Overview

Excel OM2 multimode cables are made of a high grade bend-insensitive graded-index fibre. Transmission speeds of 10/Mb/s, 100Mb/s, 1 Gb/s and 10 Gb/s are supported and the fibre is compatible with all types of OM2 optical fibre. It has a 50 µm core with 125 µm cladding diameter.

### Cores Colours

1. Red	2. Green	3. Blue	4. Yellow
5. White	6. Grey	7. Brown	8. Violet
9. Turquoise	10. Black	11. Orange	12. Pink
13. Yellow with mark every 70 mm	14. White with mark every 70 mm	15. Grey with mark every 70 mm	16. Turquoise with mark every 70 mm
17. Orange with mark every 70 mm	18. Pink with mark every 70 mm	19. Yellow with mark every 35 mm	20. White with mark every 35 mm
21. Grey with mark every 35 mm	22. Turquoise with mark every 35 mm	23. Orange with mark every 35 mm	24. Pink with mark every 35 mm

### Physical Properties

Property	Test method	Value
Permanent tensile strength	IEC 60974-1-2 E11	4, 6, 8 & 12 cores 500 N

		16 cores	1000 N
		24 cores	1500 N
Short term tensile strength (some days)	IEC 60974-1-2 E11	4, 6, 8 & 12 cores	1000 N
		16 cores	1400 N
		24 cores	1600 N
Maximum installation load (a few hours)		4, 6, 8 & 12 cores	1500 N
		16 cores	2100 N
		24 cores	2400 N
Impact	IEC 60974-1-2 E4		20 J
Crush (compressive strength)	IEC 60974-1-2 E3		3000 N / 100 mm
Torsion	IEC 60974-1-2 E7		5 cycles ± 1 turn
Temperature range	IEC 60974-1-2 F1	Operation & installation	-20°C to +70°C
		Storage	-40°C to +70°C

Property	4 Core	6 Core	8 Core	2 Core	16 Core	24 Core
Heat of combustion	760 MJ/km	845 MJ/km	970 MJ/km	1180 MJ/km	1400 MJ/km	1700 MJ/km
	0.21 KWh/m	0.23 KWh/m	0.29 KWh/m	0.33 KWh/m	0.39 KWh/m	0.47 KWh/m
Nominal diameter	6.5 mm	6.6 mm	7.0 mm	7.0 mm	8.0 mm	8.5 mm
Nominal cable weight	34 kg/km	36 kg/km	39 kg/km	43 kg/km	52 kg/km	63 kg/km
Minimum bend radius						
Long term	100 mm	100 mm	100 mm	130 mm	130 mm	230 mm
Short term	50 mm	50 mm	50 mm	75 mm	75 mm	115 mm

Property		
Fibre	Tight buffered fibres 900 µm ± 50 µm	
Strength member	E-Glass rovings	
Jacket	1.1 mm black, Halogen free, flame resistant thermoplastic sheathing compound acc. to EN 50290-2-27, UV stabilised	
Fire rating	IEC 60332-1-2 IEC 60754-1 IEC 60754-2 IEC 61034-2	Single vertical wire test No halogens No acid matters No dense smoke

## Performance Properties

Cable attenuation	IEC 60793-1-40
Maximum attenuation value of cable at 850 nm	≤ 2.7 dB/km
Maximum attenuation value of cable at 1300 nm	≤ 0.8 dB/km
Typical value at 850 nm	≤ 2.5 dB/km
Typical value at 1300 nm	≤ 0.6 dB/km
Inhomogeneity of OTDR trace for any two 1000 metre fibre lengths	Max. 0.1 dB/km
Fibre bending loss R=7.5 mm 850/1300 nm	≤ 0.2 dB / ≤ 0.5 dB
Fibre bending loss R=15 mm 850/1300 nm	≤ 0.1 dB / ≤ 0.3 dB

Bandwidth	IEC 60793-1-41
Overfilled (OFL) modal bandwidth at 850 nm	≥ 500 MHz.km
Overfilled (OFL) modal bandwidth at 1300 nm	≥ 500 MHz.km

Standards and Norms	
IEC 60793-2-10: type A1a.1	EN 50173-1 category OM2.
ITU G.651.1	ISO / IEC 11801 category OM2
IEEE 802.3	TIA / EIA-492 AAAB
EN 60793-2-10: type A1a.1	ANSI / TIA / EIA-568-C

Property	Standard	Value
Core diameter	IEC / EN 60793-1-20	50.0 ± 1.0 µm
Core non-circularity	IEC / EN 60793-1-20	≤ 5 %
Cladding diameter	IEC / EN 60793-1-20	125.0 ± 1.0 µm
Cladding non-circularity	IEC / EN 60793-1-20	≤ 0.7 %

Core - cladding concentricity error	IEC / EN 60793-1-20	≤ 1.0 μm
Primary coating diameter - uncoloured	IEC / EN 60793-1-21	242 ± 5 μm
Primary coating diameter - coloured	IEC / EN 60793-1-21	250 ± 15 μm
Primary coating non-circularity	IEC / EN 60793-1-21	≤ 5 %
Primary coating - cladding concentricity error	IEC / EN 60793-1-21	≤ 6 μm
Group index of refraction:	IEC / EN 60793-1-22	
	at 850 nm	1.482
	at 1300 nm	1.477
Proof stress level	IEC / EN 60793-1-30	≥ 0.7 (≈ 1 % strain) Gpa
Typical average stripforce	IEC / EN 60793-1-32	1.7 N
Strip force (peak)	IEC / EN 60793-1-32	1.3 ≤ F <sub>peak.strip</sub> ≤ 8.9 N
Numerical aperture	IEC / EN 60793-1-43	0.200 ± 0.015

### Typical Applications

- 100BASE-FX
- 100BASE-SX
- 100BASE-LX
- FDDI
- 155 Mbps ATM
- 622 Mbps ATM
- 531 Mbps Fibre Channel
- 1062 Mbps Fibre Channel

### Part Number Information

Part No.	Description
200-115	Internal/External Grade Tight Buffered Fibre Cable 4 Core 50/125 OM2
200-117	Internal/External Grade Tight Buffered Fibre Cable 6 Core 50/125 OM2
200-135	Internal/External Grade Tight Buffered Fibre Cable 8 Core 50/125 OM2
200-145	Internal/External Grade Tight Buffered Fibre Cable 12 Core 50/125 OM2
200-146	Internal/External Grade Tight Buffered Fibre Cable 16 Core 50/125 OM2
200-147	Internal/External Grade Tight Buffered Fibre Cable 24 Core 50/125 OM2

### System Warranty

The Excel System Warranty provides a 25-year product and applications assurance of compliance with the industry performance standard appropriate to the class of cabling installed. The warranty may be applied for by an accredited Excel Partner who has designed, supplied and installed the said system.



#### S-Cabling Sp. z o.o.

ul. Kakolewska 21, , Leszno, , 64-100, Poland

Tel: + 48 65 528 71 99 Fax:

Email: [s-cabling@s-cabling.pl](mailto:s-cabling@s-cabling.pl) Web: [www.s-cabling.pl](http://www.s-cabling.pl)

# S-Cabling